


Morely Red Dragfaced

MRD



CAMTECH



NEN-EN 771-1, APRIL 2013, AND NEN-EN 771-1/A1, MARCH 2005 CATEGORY 1, HD CLAY BRICKS PRODUCTION REFERENCE CODE: MALPESA Klinker Red Dragfaced	
LENGTH:	215mm, T2 (+/- 4mm), R2
WIDTH:	102mm, T2 (+/- 3mm), R2
THICKNESS:	65mm, T2 (+/- 2mm), R2
APPEARANCE:	Multi-Perforated Wirecut - Euro group 1
AVERAGE COMPRESSIVE STRENGTH:	> 50 N/mm ²
DIMENSIONAL STABILITY:	NPD
BOND STRENGTH:	NPD
ACTIVE SOLUBLE SALTS:	S2
REACTION TO FIRE:	EURO CLASS A1
WATER ABSORPTION:	<6% m/md
INITIAL RATE OF WATER ABSORPTION:	IW4 STRONG SUCTION, >4.0kg/m ² .min
WATER VAPOUR DIFFUSION COEFFICIENT:	50/100
GROSS DRY DENSITY:	1335kg/m ³ , D1 (10%, +/- 133.5kg/m ³)
THERMAL CONDUCTIVITY:	0,39 W/mK
FREEZE/THAW RESISTANCE:	F2

NOTE:

DIMENSIONS MAY VARY DEPENDING ON THE PRODUCTION. FOR THE MOST RECENT VERSION SEE WWW.CAMTECHBP.CO.UK. THIS DOCUMENT IS NOT BINDING AND ANNULS ALL PREVIOUS PUBLICATIONS. THE MANUFACTURER RESERVES THE RIGHT TO CHANGE THE PRODUCT RANGE AND CHARACTERISTICS. THE USER MUST ALWAYS CHECK THAT THEY HAVE THE MOST RECENT DESCRIPTIVE TEXT.

SHOWROOM & HEAD OFFICE:

21/23 JARMAN WAY, ROYSTON, HERTFORDSHIRE, SG8 5HW

01763 262 006